

Aradur® 3986[#]

Modified polyamine adduct dissolved in water

Applications Used with liquid epoxy resins such as Araldite® GY 776, PY 756 or liquid resin emulsion PZ 756/67, Aradur 3986 is suitable for the formulation of water-based coatings for application to mineral and metallic substrates.

- Properties** Used along with suitable epoxy resins, Aradur 3986 presents the following features:
- Contains no volatile amines or solvents
 - light-coloured films with low yellowing under the effect of UV rays
 - pot life range up to four hours depending on solids/filler content
 - higher solids formulations show visible end of potlife
 - very fast drying and hardening due to rapid chemical curing
 - no flash rust inhibitor necessary
 - good chemical resistance
 - very good protection against corrosion

| | | | |
|-----------------|--------------------------------------------------------------------------|--------------------------------------------------|-------------------|
| Key data | Specified key data | | |
| | Aspect (visual) | clear or slightly hazy colloidal solution | |
| | Colour Gardner (ISO 4630) | ≤ 6 | |
| | Amine number (ISO 9702) | 90 - 110 | [mg KOH/g] |
| | Solids content (Karl Fischer titration of water content, ISO 760) | 39 - 41 | [%] |
| | Viscosity at 25 °C (Rotary viscosity, ISO 3219) | 15000 - 35000 | [mPa s] |


Specified key data are individually checked throughout and guaranteed.

| | | |
|-----------------------------------------------------------------------------------------------|------------------------------------------------------------------------------------|----------------------|
| Typical key data | | |
| H ⁺ active Equivalent | ~ 415 | [g/Eq] |
| Density at 20 °C (ISO 1675) | 1,06 | [g/cm ³] |
| Solvent | water | |
| Flash point (Pensky Martens, ISO 2719) | > 100 | [°C] |
| As-supplied form | liquid | |
| Odour | weak | |
| Shelf life (at storage temperature between 2 - 40 °C) (see expiry date on original container) | several years | |
| Hazardous decomposition products (when disposed of in fire) | carbon monoxide, carbon dioxide, nitrogen oxides and other toxic gases and vapours | |
| Disposal | regular procedures approved by local authorities | |

Typical key data are spot checked; the values are typical for the product and are indicated for information only. The values are not guaranteed.

[#] In addition to the brand name product denomination may show different appendices, which allows us to differentiate between our production sites: e.g. BD = Germany, US = United States, IN = India, CI = China, etc. These appendices are in use on packaging, transport and invoicing documents. Generally the same specifications apply for all versions. Please address any additional need for clarification to the appropriate Huntsman contact.

| | |
|-----------------------------|--------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| Mixing ratios | <p>Araldite GY 776 with Aradur 3986 is 100:220 parts by weight</p> <p>Araldite PZ 756/67 with Aradur 3986 is 100:155 parts by weight</p> <p>Variation of up to 10 % can be tolerated. An excess of hardener will increase flexibility and adhesion, while improved levels of anti-corrosion protection are achieved with a lower proportion of hardener.</p> |
| Storage | <p>Aradur 3986 should be stored in a dry place, preferably in the sealed original container, at temperatures between 2 and 40 °C (temperature should never be allowed to drop below 0 °C). The product should not be stored exposed to direct sunlight.</p> |
| Handling precautions | <p>Mandatory and recommended industrial hygiene procedures should be followed whenever our products are being handled and processed. For additional information please consult the corresponding product safety data sheets and the brochure "Hygienic precautions for handling plastics products".</p> |
| Note | <p>Aradur[®] is a registered trademark of Huntsman LLC or an affiliate thereof.</p> |

| | |
|-----------------------------------------------------------------------------------------------------------------------------|-------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| <p>Huntsman LLC [®]Registered trademark</p> | <p>IMPORTANT: The following supersedes Buyer's documents. SELLER MAKES NO REPRESENTATION OR WARRANTY, EXPRESS OR IMPLIED, INCLUDING OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. No statements herein are to be construed as inducements to infringe any relevant patent. Under no circumstances shall Seller be liable for incidental, consequential or indirect damages for alleged negligence, breach of warranty, strict liability, tort or contract arising in connection with the product(s). Buyer's sole remedy and Seller's sole liability for any claims shall be Buyer's purchase price. Data and results are based on controlled or lab work and must be confirmed by Buyer by testing for its intended conditions of use. The product(s) has not been tested for, and is therefore not recommended for, uses for which prolonged contact with mucous membranes, abraded skin, or blood is intended; or for uses for which implantation within the human body is intended.</p> |
|  <p>APPROVED TO ISO 9001</p> | |