

Huntsman Advanced Materials Americas Inc.  
5121 San Fernando Road West  
Los Angeles, CA 90039  
818.247.6210

Customer Service Hotline: 800.367.8793  
Customer Service Faxline: 517.351.6255  
Technical Inquiries: 800.817.8260



website: [www.araldite.com](http://www.araldite.com)  
e-mail: [adhesives\\_group@huntsman.com](mailto:adhesives_group@huntsman.com)

## Product Data

# ARALDITE<sup>®</sup> AV 1253 Resin Hardener HV 1253 CARVABLE EPOXY PASTE FOR WOOD

**DESCRIPTION:** Araldite AV 1253 resin/Hardener HV 1253 epoxy adhesive is a carvable paste especially suited for bonding and repairing wood. Mahogany in color, it is easy to saw, carve, drill, tap and work with woodworking tools. The two-component epoxy system is color coded to facilitate thorough mixing and has an easy-to-use, one-to-one (by volume) mixing ratio. Although it is recommended for repairing and bonding wood products, the epoxy system can also be used to bond metals and other substrates.

TYPICAL PROPERTIES:	<u>Property</u>	<u>Test Method</u>	<u>Test Values<sup>(1)</sup></u>	
			<u>Resin</u>	<u>Hardener</u>
	Color/Form	Visual	Brown Paste	Light Purple Paste
	Specific Gravity	ASTM D-792	0.82	0.64
	Resistance @ 77°F (25°C)		Pass 1 in. (2.5 cm) Fail 1.25 in. (3.2 cm)	Pass 0.5 in. (1.25 cm) Fail 0.75 in. (1.9 cm)

TYPICAL MIXED PROPERTIES:	<u>Property</u>	<u>Test Method</u>	<u>Test Values<sup>(1)</sup></u>
	Resin/Hardener Ratio (by weight)	ASTM D-2471	100/82
	Resin/Hardener Ratio (by volume)		100/100
	Pot Life @ 77°F (25°C)		20 min.
	Sag Resistance @ 77°F (25°C)		Pass 0.5 in. (1.25 cm) Fail 1 in. (2.5 cm)

CURE SCHEDULES:	<u>Temperature</u>	<u>Cure Time</u>
	77°F (25°C)	6 hrs.
140°F (60°C)	30 minutes	
212°F (100°C)	10 minutes	
302°F (150°C)	10 minutes	

**TYPICAL CURED  
PROPERTIES:**

**Lap Shear Strength Effect of Time and Temperature**

<u>Cure Temperature</u>	<u>Exposure Time</u>	<u>Shear Strength</u>	
		<u>psi</u>	<u>MPa</u>
77°F (25°C)	4 hrs	1560	11
	8 hrs	1990	14
	24 hrs	2280	16
140°F (60°C)	10 min	1560	11
	20 min	1990	14
	30 min	1990	14
212°F (100°C)	5 min	1710	12
	10 min	1850	13
	20 min	1850	13
	30 min	1990	14
302°F (150°C)	5 min	1710	12
	10 min	1850	13
	20 min	1850	13
	30 min	1850	13

**TYPICAL CURED  
PROPERTIES:**

***Effect of Test Temperature***

Load applied 10 minutes after joint test temperature - cured 20 min at 212°F (100°C).

<u>Cure Temperature</u>	<u>Shear Strength</u>	
	<u>psi</u>	<u>MPa</u>
-76°F (-60°C)	1710	12
77°F (25°C)	1990	14
176°F (80°C)	140	1

**Properties of Araldite AV-1253 resin/Hardener HV-1253**

Cured 7 days @ 77°F (25°C)

**Deflection Temperature, °F (°C) (ASTM D-648) @ 66 psi** 124 (51)

<u>Property</u>	<u>Test Method</u>	<u>psi MPa</u>	
Compressive Properties	(ASTM D-695) @ 77°F (25°C)		
Strength - ultimate		4120	29
Strength – 0.02% offset		2840	20
Modulus of elasticity		161000	1130
Tensile Properties	(ASTM D-638) @ 77°F (25°C)		
Strength - ultimate		2130	15
Strength – 0.02% offset		1850	13
Modulus of elasticity		140000	985
Flexural Properties	(ASTM D-790) @ 77°F (25°C)		
Strength - ultimate		4270	30
Modulus of elasticity		149000	1050

Tested @ 77°F (25°C), unless otherwise noted.

## CAUTION:

Huntsman Advanced Materials Americas Inc. maintains up-to-date Material Safety Data Sheets (MSDS) on all of its products. These sheets contain pertinent information that you may need to protect your employees and customers against any known health or safety hazards associated with our products. Users should review the latest MSDS to determine possible health hazards and appropriate precautions to implement prior to using this material. Copies of the latest MSDS may be requested by calling our customer service group at 800-367-8793 or emailing your request to [adhesives\\_group@huntsman.com](mailto:adhesives_group@huntsman.com).

## FIRST AID!

Eyes and skin: Flush eyes with water for 15 minutes. Contact a physician if irritation persists. Wash skin thoroughly with soap and water. Remove and wash contaminated clothing before reuse.

Inhalation: Remove subject to fresh air.

Swallowing: Dilute by giving water to drink and contact a physician promptly. Never give anything to drink to an unconscious person.

## KEEP OUT OF REACH OF CHILDREN

## FOR PROFESSIONAL AND INDUSTRIAL USE ONLY

### **IMPORTANT LEGAL NOTICE:**

Sales of a referenced product ("Product") are subject to the general terms and conditions of sale of Huntsman Advanced Materials Americas Inc. ("Huntsman").

**WARRANTY:** Huntsman warrants to the Buyer that the Product will conform to the published specifications for that Product at the time of manufacture, and that the Product will be free from defects in material and workmanship in normal use.

**DISCLAIMER AND LIMITATION OF LIABILITY:** EXCEPT AS SET FORTH ABOVE, SELLER MAKES NO WARRANTY OR REPRESENTATION, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Huntsman cannot control Buyer's application and use of the Product and accepts no responsibility therefore. No statement or recommendation contained in any Product literature may be construed as a representation about the suitability of a Product for the particular application of Buyer or user or as an inducement to infringe any relevant patent. Buyer is responsible to ensure that its intended use of the Product does not infringe any third-party's intellectual property rights. Seller neither assumes, nor authorizes any representative or other person to assume for it, any obligation or liability other than as is expressly set forth herein. UNDER NO CIRCUMSTANCES SHALL HUNTSMAN BE LIABLE FOR INCIDENTAL, CONSEQUENTIAL, SPECIAL OR OTHER INDIRECT DAMAGES AS A RESULT OF A BREACH OF ANY WARRANTY OR THE FAILURE OF A PRODUCT OR ANY CLAIM THAT IS ESSENTIALLY BASED UPON SUCH BREACH OR FAILURE. Any claim by Buyer, whether arising in contract, tort, negligence, breach of warranty, strict liability, or otherwise, related to a Product shall be limited to, and the sole liability of Seller and the sole remedy of Buyer for any claims shall be for, the purchase price of the Product in respect of which such claim is made. The foregoing DISCLAIMER and LIMITATION OF LIABILITY supercedes Buyer's documents.

**WARNING:** Technical data and results are based upon tests under controlled laboratory conditions and must be confirmed by Buyer by testing for its intended conditions of use. The Product has not been tested for, and therefore is not recommended or suitable for, uses for which prolonged contact with mucous membranes, abraded skin, or blood is intended or likely, or for uses for which implantation within the human body is intended, and Huntsman assumes no liability for any such uses.

© 2004 Huntsman Advanced Materials Americas Inc.  
Araldite is a registered trademark of Huntsman LLC or an affiliate thereof in one or more, but not all, countries.