

Advanced Materials**Araldite® DY-J**

Reactive Diluent for Epoxy Resins

**Araldite® DY-J
Reactive Diluent****Key properties**

- **Very effective viscosity reducer**
- **Low volatility**
- **Reduces surface tension and improves wettability**

Description

Araldite® DY-J reactive diluent is an alkyl glycidyl ether where the alkyl groups are predominantly C₈ and C₁₀. Araldite® DY-J reactive diluent exhibits a low volatility and it is advantageous primarily as an additive to reduce the viscosity of epoxy resins.


Applications

Casting, Coatings, Filament winding, Floorings, Laminating, Electrical and Tooling


Product data*

	Araldite® DY-J Reactive Diluent
Visual Appearance	Clear, no contamination
Color, Gardner, max.	1
Epoxy Value (eq./kg)	4.0 – 4.3
Epoxy Equivalent (g/eq.)	220 – 250
Viscosity at 25°C (cP)	15
Flash Point, Closed Cup (°C)	200
Density at 25°C (g/cm ³ , lb/gal)	0.91, 7.6

* Product data are based on Huntsman's test methods. Copies are available upon request.

Chemical Structure**Formulations**

The graph below shows the effect of Araldite® GY 6010 epoxy (11000 – 14 000 cP) and Araldite® GY 6020 epoxy (16 000 – 20 000 cP) modified with Araldite® DYJ reactive diluent.

Viscosity @ 25°C (cP)

Storage

Araldite® DY-J reactive should be stored in a dry place, in the sealed original container, at temperatures between +2°C and +40°C (+35.6°F and +104°F). Under these storage conditions the shelf life is 5 years. The product should not be exposed to direct sunlight.

Precautionary Statement

Huntsman Advanced Materials Americas LLC maintains up-to-date Material Safety Data Sheets (MSDS) on all of its products. These sheets contain pertinent information that you may need to protect your employees and customers against any known health or safety hazards associated with our products. Users should review the latest MSDS to determine possible health hazards and appropriate precautions to implement prior to using this material.

First Aid!

Refer to MSDS as mentioned above.

KEEP OUT OF REACH OF CHILDREN

FOR PROFESSIONAL AND INDUSTRIAL USE ONLY

Huntsman Advanced Materials warrants only that its products meet the specifications agreed with the user. Typical properties, where stated, are to be considered as representative of current production and should not be treated as specifications.

The manufacture of materials is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication.

While all the information and recommendations in this publication are, to the best of Huntsman Advanced Material's knowledge, information and belief, accurate at the date of publication, NOTHING HEREIN IS TO BE CONSTRUED AS A WARRANTY, WHETHER EXPRESS OR IMPLIED, INCLUDING BUT WITHOUT LIMITATION, AS TO MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. IN ALL CASES, IT IS THE RESPONSIBILITY OF THE USER TO DETERMINE THE APPLICABILITY OF SUCH INFORMATION AND RECOMMENDATIONS AND THE SUITABILITY OF ANY PRODUCT FOR ITS OWN PARTICULAR PURPOSE.

The behaviour of the products referred to in this publication in manufacturing processes and their suitability in any given end-use environment are dependent upon various conditions such as chemical compatibility, temperature, and other variables, which are not known to Huntsman Advanced Materials. It is the responsibility of the user to evaluate the manufacturing circumstances and the final product under actual end-use requirements and to adequately advise and warn purchasers and users thereof.

Products may be toxic and require special precautions in handling. The user should obtain Safety Data Sheets from Huntsman Advanced Materials containing detailed information on toxicity, together with proper shipping, handling and storage procedures, and should comply with all applicable safety and environmental standards.

Hazards, toxicity and behaviour of the products may differ when used with other materials and are dependent on manufacturing circumstances or other processes. Such hazards, toxicity and behaviour should be determined by the user and made known to handlers, processors and end users.

Except where explicitly agreed otherwise, the sale of products referred to in this publication is subject to the general terms and conditions of sale of Huntsman Advanced Materials LLC or of its affiliated companies including without limitation, Huntsman Advanced Materials (Europe) BVBA, Huntsman Advanced Materials Americas Inc., and Huntsman Advanced Materials (Hong Kong) Ltd.

Huntsman Advanced Materials is an international business unit of Huntsman Corporation. Huntsman Advanced Materials trades through Huntsman affiliated companies in different countries including but not limited to Huntsman Advanced Materials LLC in the USA and Huntsman Advanced Materials (Europe) BVBA in Europe.

Aradur and Araldite are registered trademarks of Huntsman Corporation or an affiliate thereof in one or more, but not all, countries.

Copyright © 2007 Huntsman Corporation or an affiliate thereof. All rights reserved.

Huntsman Advanced Materials
10003 Woodloch Forest Drive
The Woodlands, Texas 77381

Tel: 888-564-9318
Fax: 281-719-4047
www.huntsman.com/advanced_materials