

**Advanced Materials****Araldite® LY 1564 SP\* / Aradur® 3486 / Aradur® 3487\*****WARM CURING EPOXY SYSTEM**

Araldite® LY 1564 SP

Aradur® 3486 (formulated amine hardener)

Aradur® 3487 (formulated amine hardener)

<b>APPLICATIONS</b>	Industrial composites		
<b>PROPERTIES</b>	Laminating system with low viscosity and high flexibility. The reactivity may easily be adjusted to demands through the combination of both hardeners. The long pot life of XB 3486 facilitates the production of very large industrial parts. The systems are qualified by Germanischer Lloyd.		
<b>PROCESSING</b>	<ul style="list-style-type: none"> <li>• Resin Transfer Moulding (RTM, SCRIMP)</li> <li>• Wet lay-up</li> <li>• Filament Winding</li> </ul>		
<b>KEY DATA</b>	<b>Araldite® LY 1564 SP</b>		
	Aspect (visual)	clear liquid	
	Colour (Gardner, ISO 4630)	1-2	
	Viscosity at 25 °C (ISO 12058-1)	1200 - 1400	[mPa s]
	Density at 25 °C (ISO 1675)	1.1 - 1.2	[g/cm <sup>3</sup> ]
	Flash point (ISO 2719)	185	[°C]
	Storage temperature (see expiry date on original container)	2 - 40	[°C]
	<b>Aradur® 3486</b>		
	Aspect (visual)	clear colourless to slightly yellow liquid	
	Viscosity at 25 °C (ISO 12058-1)	10 - 20	[mPa s]
	Density at 25 °C (ISO 1675)	0.94 - 0,95	[g/cm <sup>3</sup> ]
	Flash point (ISO 2719)	123	[°C]
	Storage temperature (see expiry date on original container)	2 - 40	[°C]
	<b>Aradur® 3487</b>		
	Aspect (visual)	clear colourless to slightly yellow liquid	
	Viscosity at 25 °C (ISO 12058-1B)	30 - 70	[mPa s]
	Density at 25 °C (ISO 1675)	0,98 - 1,0	[g/cm <sup>3</sup> ]
	Flash point (ISO 2719)	122 - 124	[°C]
	Storage temperature (see expiry date on original container)	2 - 40	[°C]
<b>STORAGE</b>	Provided that Araldite® LY 1564 SP and Aradur® 3486 or Aradur® 3487 are stored in a dry place in their original, properly closed containers at the above mentioned		

\* In addition to the brand name product denomination may show different appendices , which allows us to differentiate between our production sites: e.g , BD = Germany, US = United States, IN = India, CI = China, etc.. These appendices are in use on packaging, transport and invoicing documents. Generally the same specifications apply for all versions. Please address any additional need for clarification to the appropriate Huntsman contact.

---

storage temperatures they will have the shelf lives indicated on the labels.  
Partly emptied containers should be closed immediately after use.

## PROCESSING DATA

MIX RATIO	Components	Parts by weight	Parts by volume
	Araldite® LY 1564 SP	100	100
	Aradur® 3486	34	41
	Araldite® LY 1564 SP	100	100
	Aradur® 3487	34	41

We recommend that the components are weighed with an accurate balance to prevent mixing inaccuracies which can affect the properties of the matrix system. The components should be mixed thoroughly to ensure homogeneity. It is important that the side and the bottom of the vessel are incorporated into the mixing process.

When processing large quantities of mixture the pot life will decrease due to exothermic reaction. It is advisable to divide large mixes into several smaller containers.

INITIAL MIX VISCOSITY		[°C]	[mPa s]
(HOEPLER, ISO 12058-1B)	LY 1564 SP /Aradur® 3486	at 25	200 - 300
	LY 1564 SP /Aradur® 3487	at 25	220 - 320

POT LIFE		[g]	[min]
(TECAM, 23°C, 65 % RH)	LY 1564 SP /Aradur® 3486	100	560 - 620
		1000	180 - 230
	LY 1564 SP /Aradur® 3487	100	130 - 160
		1000	75 - 100

GEL TIME		[°C]	[min]
(HOT PLATE)	LY 1564 SP /Aradur® 3486	at 60	110 - 130
		at 80	33 - 43
		at 100	13 - 17
		at 120	5 - 9
	LY 1564 SP /Aradur® 3487	at 60	65 - 85
		at 80	18 - 25
		at 100	6 - 10
		at 120	2 - 5

The values shown are for small amounts of pure resin/hardener mix. In composite structures the gel time can differ significantly from the given values depending on the fibre content and the laminate thickness.

## COMBINATION OF THE HARDENERS

Araldite® LY 1564 SP	100	100	100	100	100
Aradur® 3486		8.5	17	25.5	34
Aradur® 3487	34	25.5	17	8.5	
Pot Life (Tecam at 23 °C)	[min]	[min]	[min]	[min]	[min]
100g	130 - 170	290 - 340	380 - 430	530 - 590	560 - 620
Gel time (Hot plate)	[min]	[min]	[min]	[min]	[min]
at 80 °C	18 - 25	20 - 27	25 - 33	30 - 39	33 - 43
at 100 °C	6 - 10	7 - 11	9 - 13	11 - 15	13 - 17

## PROPERTIES OF THE CURED, NEAT FORMULATION

<b>GLASS TRANSITION TEMPERATURE</b>	<i>Cure:</i>	$T_g$	<i>LY 1564 Aradur® 3487</i>	<i>LY 1564 Aradur® 3486</i>	
(IEC 1006, DSC, 10 K/MIN)	2 days 23 °C	[°C]	42 - 48	33 - 37	
	8 days 23 °C	[°C]	54 - 59	49 - 53	
	20 h 40 °C	[°C]	63 - 68	52 - 56	
	15 h 50 °C	[°C]	68 - 73	66 - 70	
	24 h 50 °C	[°C]	71 - 75	66 - 70	
	10 h 60 °C	[°C]	72 - 76	67 - 71	
	16 h 60 °C	[°C]	75 - 80	68 - 72	
	4 h 80 °C	[°C]	81 - 86	77 - 81	
	8 h 80 °C	[°C]	81 - 86	80 - 84	
	2 h 100 °C	[°C]	81 - 86	78 - 82	
	5 h 100 °C	[°C]	82 - 86	80 - 84	
<b>TENSILE TEST</b> (ISO 527)	<i>LY 1564 SP / Aradur® 3487</i>		<i>Cure:</i> 15 h 50 °C	<i>Cure:</i> 8 h 80 °C	
	Tensile strength	[MPa]	77 - 81	72 - 76	
	Elongation at tensile strength	[%]	3.9 - 4.1	4.5 - 4.9	
	Ultimate strength	[MPa]	58 - 64	63 - 68	
	Ultimate elongation	[%]	7.2 - 8.0	8.0 - 9.0	
	Tensile modulus	[MPa]	3200 - 3350	2940 - 3100	
<b>TENSILE TEST</b> (ISO 527)	<i>LY 1564 SP / Aradur® 3486</i>		<i>Cure:</i> 15 h 50 °C	<i>Cure:</i> 8 h 80 °C	
	Tensile strength	[MPa]	74 - 78	70 - 74	
	Elongation at tensile strength	[%]	4.0 - 4.2	4.6 - 5.0	
	Ultimate strength	[MPa]	62 - 68	60 - 64	
	Ultimate elongation	[%]	5.8 - 6.2	8.0 - 8.5	
	Tensile modulus	[MPa]	3100 - 3250	2860 - 3000	
<b>FLEXURAL TEST</b> (ISO 178)	<i>LY 1564 SP / Aradur® 3487</i>		<i>Cure:</i> 7 days 23 °C	<i>Cure:</i> 15 h 50 °C	<i>Cure:</i> 8 h 80 °C
	Flexural strength	[MPa]	98 - 112	125 - 138	118 - 130
	Elongation at flexural strength	[%]	2.7 - 3.6	5.0 - 5.4	5.5 - 6.5
	Ultimate strength	[MPa]	98 - 112	88 - 95	88 - 100
	Ultimate elongation	[%]	2.7 - 3.6	8.2 - 10.0	10.0 - 12.0
	Flexural modulus	[MPa]	3460 - 3660	3200 - 3400	2950 - 3100
<b>FLEXURAL TEST</b> (ISO 178)	<i>LY 1564 SP / Aradur® 3486</i>		<i>Cure:</i> 7 days 23 °C	<i>Cure:</i> 15 h 50 °C	<i>Cure:</i> 8 h 80 °C
	Flexural strength	[MPa]	80 - 90	120 - 135	118 - 130
	Elongation at flexural strength	[%]	2.1 - 2.5	5.2 - 5.6	5.5 - 6.5
	Ultimate strength	[MPa]	80 - 90	78 - 85	88 - 100
	Ultimate elongation	[%]	2.1 - 2.5	9.0 - 11.5	10.5 - 12.5
	Flexural modulus	[MPa]	3500 - 3700	3100 - 3300	2900 - 3050
<b>FRACTURE PROPERTIES</b>	<i>Cure: 5 h 100 °C</i>		<i>LY 1564 SP XB 3487</i>	<i>LY 1564 SP XB 3486</i>	
<b>BEND NOTCH TEST</b> (PM 258-0/90)	Fracture toughness $K_{1C}$	[MPa√m]	0.95 - 1.05	0.95 - 1.05	
	Fracture energy $G_{1C}$	[J/m <sup>2</sup> ]	255 - 305	260 - 310	

## PROPERTIES OF THE CURED, REINFORCED FORMULATION

<b>INTERLAMINAR SHEAR TEST</b> (ASTM D 2344)	Short beam: Laminate comprising 12 layers unidirectional E-glass fabric (425 g/m <sup>2</sup> ) Laminate thickness $t = 3.0 - 3.2$ mm Fibre volume content: 63 - 65 %			
	<i>Cure: 1.5 h 80 °C + 5 h 100 °C</i>		<i>LY 1564 Aradur 3487</i>	<i>LY 1564 Aradur 3486</i>
	Shear strength	[MPa]	53 - 58	53 - 58

---

**HANDLING  
PRECAUTIONS****Personal hygiene***Safety precautions at workplace*

protective clothing	yes
gloves	essential
arm protectors	recommended when skin contact likely
<u>goggles/safety glasses</u>	<u>yes</u>

*Skin protection*

before starting work	Apply barrier cream to exposed skin
<u>after washing</u>	<u>Apply barrier or nourishing cream</u>

*Cleansing of contaminated skin*

Dab off with absorbent paper, wash with warm water and alkali-free soap, then dry with disposable towels. Do not use solvents

*Disposal of spillage*

Soak up with sawdust or cotton waste and deposit in plastic-lined bin

*Ventilation*

of workshop	Renew air 3 to 5 times an hour
of workplaces	Exhaust fans. Operatives should avoid inhaling vapours

**FIRST AID**

Contamination of the *eyes* by resin, hardener or mix should be treated immediately by flushing with clean, running water for 10 to 15 minutes. A doctor should then be consulted.

Material smeared or splashed on the *skin* should be dabbed off, and the contaminated area then washed and treated with a cleansing cream (see above). A doctor should be consulted in the event of severe irritation or burns. Contaminated clothing should be changed immediately.

Anyone taken ill after *inhaling* vapours should be moved out of doors immediately.

In all cases of doubt call for medical assistance.

---

**IMPORTANT LEGAL NOTICE**

Huntsman Advanced Materials warrants only that its products meet the specifications agreed with the user. Typical properties, where stated, are to be considered as representative of current production and should not be treated as specifications.

The manufacture of materials is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication.

While all the information and recommendations in this publication are, to the best of Huntsman Advanced Material's knowledge, information and belief, accurate at the date of publication, NOTHING HEREIN IS TO BE CONSTRUED AS A WARRANTY, WHETHER EXPRESS OR IMPLIED, INCLUDING BUT WITHOUT LIMITATION, AS TO MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. IN ALL CASES, IT IS THE RESPONSIBILITY OF THE USER TO DETERMINE THE APPLICABILITY OF SUCH INFORMATION AND RECOMMENDATIONS AND THE SUITABILITY OF ANY PRODUCT FOR ITS OWN PARTICULAR PURPOSE.

The behaviour of the products referred to in this publication in manufacturing processes and their suitability in any given end-use environment are dependent upon various conditions such as chemical compatibility,

temperature, and other variables, which are not known to Huntsman Advanced Materials. It is the responsibility of the user to evaluate the manufacturing circumstances and the final product under actual end-use requirements and to adequately advise and warn purchasers and users thereof.

Products may be toxic and require special precautions in handling. The user should obtain Safety Data Sheets from Huntsman Advanced Materials containing detailed information on toxicity, together with proper shipping, handling and storage procedures, and should comply with all applicable safety and environmental standards.

Hazards, toxicity and behaviour of the products may differ when used with other materials and are dependent on manufacturing circumstances or other processes. Such hazards, toxicity and behaviour should be determined by the user and made known to handlers, processors and end users.

Except where explicitly agreed otherwise, the sale of products referred to in this publication is subject to the general terms and conditions of sale of Huntsman Advanced Materials LLC or of its affiliated companies including without limitation, Huntsman Advanced Materials (Europe) BVBA, Huntsman Advanced Materials Americas Inc., and Huntsman Advanced Materials (Hong Kong) Ltd.

Huntsman Advanced Materials is an international business unit of Huntsman Corporation. Huntsman Advanced Materials trades through Huntsman affiliated companies in different countries including but not limited to Huntsman Advanced Materials LLC in the USA and Huntsman Advanced Materials (Europe) BVBA in Europe.

Aradur and Araldite are registered trademarks of Huntsman Corporation or an affiliate thereof.

Copyright © 2007 Huntsman Corporation or an affiliate thereof. All rights reserved.

Main Office :  
**Huntsman Advanced Materials (Switzerland) GmbH**  
Klybeckstrasse 200  
4057 BASEL  
Switzerland  
+41 61 966 3333