

Product	Datasheet	Property Name	Property Value
Arathane® CW 5620 / Arathane® HY 5610	Datasheet available on request	Min. curing time (h)	24/25 or 6/80
		Type of system	prefilled
		Density of casting (g/cm ³)	1.44
		Mixing ratio (pbw)	100/22
		Viscosity: resin; hardener; mixture (min @ °C)	1 700/25;420/25;1 800/25
		Pot life (min @ °C)	45/25
		Gel time (min @ °C)	70/25
		Glass transition temperature (°C)	20
		Thermal conductivity, 25°C (W/mk)	0.50
		Flammability (UL 94)	V-0; 6 mm
		Thermal Class	B
		Shore D hardness, 23°C	40
		Tensile strength / flexural strength, 23°C (MPa)	7/ n.a.
		Elongation at break, 23°C (%)	70
		Modulus of elasticity, 23°C (MPa)	21
		Water absorption, 10 d / 23°C, 30 min / 100°C (%)	0.50 / 0.33
		Dielectric dissipation factor tan, 50 Hz/23°C (%)	11.0
		Relative permittivity, 50Hz/23°C (kV/ mm)	6.0
		Dielectric strength, 23°C (kV/mm)	25

[Back to Product Selector](#)