



ECCOBOND 45 Clear/Catalyst 15 Clear

October 2011

PRODUCT DESCRIPTION

ECCOBOND 45 Clear/Catalyst 15 Clear provides the following product characteristics:

Technology	Epoxy
Technology (Catalyst)	Amine
Appearance (Resin)	Clear yellow
Appearance (Catalyst)	Clear yellow
Mix Ratio - Resin : Hardener	100 : 100
Rigid Formula	
Mix Ratio - Resin : Hardener	100 : 200
Semi-Rigid Formula	
Mix Ratio - Resin : Hardener	100 : 300
Flexible Formula	
Product Benefits	<ul style="list-style-type: none"> • Unfilled • Ease of use • Non-conductive • General purpose • Controllable flexibility • Bond dissimilar substrates
Cure	Heat cure
Application	Assembly

ECCOBOND 45 Clear/Catalyst 15 Clear is a clear, unfilled epoxy adhesive which, by varying the amount of catalyst used, can adjust the hardness from flexible to rigid. It has an easy mix ratio and bonds well to a wide variety of substrates. ECCOBOND 45 Clear/Catalyst 15 Clear is the clear, unfilled version of ECCOBOND 45/Catalyst 15.

ECCOBOND 45 Clear/Catalyst 15 Clear can be used with a variety of catalysts. For more information on mixed properties when used with other available catalysts, please contact your local technical service representative for assistance and recommendations.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Part A Properties 45 Clear

Viscosity, Brookfield , ASTM D2393, mPa·s (cP)	13,500
Density, ASTM D792, g/cm ³	1.17
Flash Point - See MSDS	

Part B Properties Catalyst 15

Viscosity, Brookfield , ASTM D2393, mPa·s (cP)	25,000
Density, ASTM D792, g/cm ³	0.97
Flash Point - See MSDS	

Mixed Properties

Rigid Formulation:

Viscosity, Brookfield , ASTM D2393, mPa·s (cP)	20,000
Density, ASTM D792, g/cm ³	1.06

Work Life, 100 grams @ 25°C, minutes	120
Flash Point - See MSDS	

Semi-Rigid Formulation:

Viscosity, Brookfield , ASTM D2393, mPa·s (cP)	20,000
Density, ASTM D792, g/cm ³	1.03
Work Life, 100 grams @ 25°C, minutes	140
Flash Point - See MSDS	

Flexible Formulation:

Viscosity, Brookfield , ASTM D2393, mPa·s (cP)	21,000
Density, ASTM D792, g/cm ³	1.01
Work Life, 100 grams @ 25°C, minutes	160
Shelf Life @ 25 °C, months	12
Flash Point - See MSDS	

TYPICAL CURING PERFORMANCE

Cure Schedule

15 to 30 minutes @ 105°C
2 to 4 hours @ 65°C
4 to 6 hours @ 45°C
16 to 24 hours @ 25°C

The above cure profiles are guideline recommendations. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF CURED MATERIAL

Rigid Formulation

Physical Properties:

Hardness, Shore D, ATSM D2240	75
Flexural strength , ASTM D790	N/mm ² 57 (psi) (8,300)
Temperature Range of Use, °C	-40 to 90

Electrical Properties:

Volume Resistivity @ 25°C, ASTM D257, ohm-cm	>1×10 ¹³
Dielectric Strength , ASTM D149, kV/mm	16
Dielectric Constant @ 1MHz, ASTM D150	3
Dissipation Factor @ 1MHz, ASTM D150	0.03

Semi-rigid Formulation

Physical Properties:

Hardness, Shore D, ATSM D2240	52
Temperature Range of Use, °C	-55 to 80



Electrical Properties:

Volume Resistivity @ 25°C, ASTM D257, ohm-cm	>1×10 ¹³
Dielectric Strength, ASTM D149, kV/mm	16
Dielectric Constant @ 1MHz, ASTM D150	3.0
Dissipation Factor @ 1MHz, ASTM D150	0.03

Flexible Formulation

Physical Properties:

Hardness, Shore A, ASTM D2240	45
Temperature Range of Use, °C	-55 to 65

Electrical Properties:

Volume Resistivity @ 25°C, ASTM D257, ohm-cm	>1×10 ¹⁰
Dielectric Strength, ASTM D149, kV/mm	16
Dielectric Constant @ 1MHz, ASTM D150	3.0
Dissipation Factor @ 1MHz, ASTM D150	0.03

TYPICAL PERFORMANCE OF CURED MATERIAL

Rigid Formulation

Shear Strength:

Tensile Lap Shear Strength, ASTM D1002:		
Aluminum to aluminum @ 25 °C	N/mm ²	16.5
	(psi)	(2,400)

GENERAL INFORMATION

For safe handling information on this product, consult the Material Safety Data Sheet, (MSDS).

DIRECTIONS FOR USE

1. Complete cleaning of the substrates should be performed to remove contamination such as oxide layers, dust, moisture, salt and oils which can cause poor adhesion or corrosion in a bonded part.
2. Some separation of components is common during shipping and storage. For this reason, it is recommended that the contents of the shipping container be thoroughly mixed prior to use.
3. Power mixing is preferred to ensure a homogeneous product.
4. Accurately weigh resin and hardener into a clean container in the recommended ratio. Weighing apparatus having an accuracy in proportion to the amounts being weighed should be used.
5. Blend components by hand, using a kneading motion, for 2 to 3 minutes and scrape the bottom and sides of the mixing container frequently to produce a uniform mixture.
6. If possible, power mix for an additional 2 to 3 minutes. Avoid high mixing speeds which could entrap excessive amounts of air or cause overheating of the mixture resulting in reduced working life.
7. Apply adhesive to all surfaces to be bonded and join together.
8. In most applications only contact pressure is required.

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage: 25 °C

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

Conversions

(°C x 1.8) + 32 = °F
 kV/mm x 25.4 = V/mil
 mm / 25.4 = inches
 N x 0.225 = lb
 N/mm x 5.71 = lb/in
 N/mm² x 145 = psi
 MPa x 145 = psi
 N·m x 8.851 = lb·in
 N·m x 0.738 = lb·ft
 N·mm x 0.142 = oz·in
 mPa·s = cP

Note

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation and its affiliates ("Henkel") specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel products. Henkel specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

All trademarks in this document are trademarks and/or registered trademarks of Henkel in the US and elsewhere.

Reference 0.0