

EpoPro[®] 104A/B30



2 PART MULTIPURPOSE EPOXY ADHESIVE & POTTING SYSTEM

EpoPro[®] 104A/B30 is a two part epoxy system that cures at room temperature or with heat into a tough adhesive & potting compound. The cured polymer provides excellent mechanical and electrical properties, and is resistant to moisture and many chemicals. The EpoPro 104A/B30 demonstrates excellent adhesion to most materials including metals, wood, rubber, glass, and many plastics.

A unique feature of this system is that the hardness of the cured polymer can be controlled by varying the mix ratio of the 104A & 104B30. The cured polymer can be varied from a hard, rigid polymer to a softer, more semi-flexible state by varying the mix ratio.

The EpoPro 104A/B30 system is available in many standard colors including translucent amber, white, black & gray. For your specific application, we can recommend custom variations of this product to fit your processing or cured property requirements. Please contact us to discuss your application if you'd like to receive samples of a custom color or to discuss the development of a custom variant that would be suitable for your application.

SUGGESTED APPLICATIONS

- Multipurpose adhesive and potting compound – excellent for many uses
- Excellent for semi-flexible, and impact resistant bonds and potting applications
- Complies with FDA 21 CFR 175.105 & 175.300 for use on food contact surfaces
- Good for potting or bonding pressure sensitive and heat sensitive devices

HANDLING PROPERTIES

	<u>VALUE</u>	<u>TEST METHOD</u>
<u>EpoPro 104A (resin)</u>		
Visual Appearance	Clear, light yellow	Visual
Density, Part A	1.15 g/cm ³	ASTM E-201
Viscosity, Part A, @ 25°C	11,000 cps	ASTM D-2393
Flash Point	>93°C	ASTM D-92
<u>EpoPro 104B30 (hardener)</u>		
Visual Appearance	Amber Liquid	Visual
Density,	0.96 g/cm ³	ASTM E-201
Viscosity, Part B, @ 25°C	16,000 cps	ASTM D-2393
Flash Point	>93°C	ASTM D-9

Mix Ratio (part by weight)

100A:50B

100A:100B

100A:150B

Product Datasheet

Viscosity Mixed @ 25°C	13,400 cps	14,500 cps	15,000 cps	ASTM D-2393
Viscosity Mixed @ 65°C	1,100 cps	1,200 cps	1,300 cps	ASTM D-2393
Pot life (100 grams) @ 25°C	30 minutes	25 minutes	35 minutes	Gardner

Cure Schedules: 6 - 12 hours @ 25°C or 1 hours @ 60°C or 20 minutes @ 80°C. Allowing the material to gel prior to curing will reduce shrinkage and increase bond strengths.

PHYSICAL PROPERTIES (Tested at 25°C unless otherwise noted)

Mix Ratio (parts by weight)	<u>100:50</u>	<u>100:100</u>	<u>100:150</u>	<u>TEST METHOD</u>
Appearance	Translucent, yellow to amber			Visual
Hardness, Shore D	85	82	76	ASTM D-2240
Tensile Strength	8,300 psi	7,500 psi	2800 psi	ASTM D-638
Tensile Elongation	3.9%	9.5%	40%	ASTM D-638
Tensile Modulus	420,000 psi	310,000 psi	-	ASTM D-638
Flexural Strength	14,000 psi	11,000 psi	-	ASTM D-790
Flexural Modulus	350,000 psi	340,000 psi	-	ASTM D-790
Compressive Yield Strength	11,500	10,400 psi	-	ASTM D-695
Izod Impact Strength notched (Ft-lb)	0.6	1.18	-	ASTM D-256
Thermal Shock Cycle from 100°C to -55°C	Passes 2 cycles	Passes 5 cycles	Pass >10 cycles	Olyphant Washer
Curing Shrinkage (linear)	0.005%	0.005%	0.003%	ASTM D-2566
Glass Transition Temperature (T _g)	81°C	72°C	57°C	ASTM D-648
Coefficient of Thermal Expansion (CTE) below T _g / above T _g (ppm/°C)	80 / 171	91 / 210	106 / 556	ASTM E-831
Weight Loss after 48 hrs @ 150°C	0.02%	0.05%	-	ASTM D-495
Moisture absorption (24 hour immersion - % weight gain)	0.16%	0.23%	-	ASTM D-570
Thermal Conductivity	0.18 W/mK	0.18 W/mK	0.18 W/mK	ASTM D-2214
Thermal Rating	105°C-130°C	105°C	90°C	EIC 216
Fungus Resistance	Non-Nutrient	Non-Nutrient	Non-Nutrient	ASTM G-21
Insulation Resistance (ohms)	>5.0 x 10 ¹⁵	3.0 x 10 ¹⁵	-	ASTM D-150
Volume Resistivity (ohm-cm)				ASTM D-150
@ 25°C	1.2 x 10 ¹⁶	3.0 x 10 ¹⁵	-	
@ 100°C	2 x 10 ¹⁰	-	-	
Dielectric Strength (V/mil)	400	380	-	ASTM D-149
Dielectric Constant @ 25C				ASTM D-150
@ 60 Hz / 10 KHz / 1 MHz	3.3/3.2/2.9	3.5/3.3/3.1	4.7/3.8/3.3	
Dissipation Factor @ 25C				ASTM D-150
@ 60 Hz / 10 KHz / 1 MHz	0.01 / 0.02 / 0.02	0.02 / 0.03 / 0.04	0.11 / 0.14 / 0.15	

Lap Shear Strength @ 25C (psi) (Mix ratio 6A:5B by weight or 1A:1B by volume) Various Substrates:	ASTM D-1002
---	-------------

Product Datasheet

Concrete	1100*	Aluminum	2000
FR-4 laminate	3200*	Galvanized Steel	1800
Polyester laminate	2800*	Copper	1650
Wood (maple)	1800*		
*Indicates substrate failure			
Effect of Temperature:			
(Aluminum lap shear panels – mix ratio 6A:5B by weight or 1A:1B by volume)			
-40°F (-40°C)	2800	105°F (40°C)	1825
67°F (20°C)	2500	150°F (65°C)	1300
77°F (25°C)	2000	180°F (82°C)	1000

NOTE: Values are based on laboratory or average production results – not for specification purposes.

FDA STATUS

Fully cured bond lines and castings made from this system comply with the requirements of the Food & Drug Administrations regulations 21 CFR 175.105 & 175.300 for the safe use on food contact surfaces under the conditions described in those sections.

NASA OUTGASSING

(After 24 hours @ 125°C and 10⁻⁶ torr per ASTM E-595)

Results will vary with cure schedule & mix ratio used. In general, lower levels of the 104B and heat cures will produce the best results.

Mix ratio	Cure Schedule	Total Mass Loss (TML) %	Collectible Condensable Volatile Materials (CCVM), %	Water Vapor Release (WVR) %
2 :1 by weight	7 days @ 25°C	0.30%	0.00%	0.35%
2 :1 by weight	30 days @ 25°C	0.25%	0.00%	0.20%
2 :1 by weight	2 hours @ 65°C	0.70%	0.40%	0.30%
2 :1 by weight	1 hours @ 93°C	0.20%	0.01%	0.19%
2 :1 by volume (100:40 by weight)	7 days @ 25°C	0.20%	0.00%	0.30%
2 :1 by volume	1 hours @ 93°C	0.22%	0.02%	0.25%
1 :1 by weight	7 days @ 25°C	0.85%	0.02%	0.40%
1 :1 by volume (6 :5 by weight)	1 hours @ 93°C	1.24%	0.05%	0.45%
100 :150 by weight	7 days @ 25°C	1.65%	0.10%	0.80%

CHEMICAL RESISTANCE

(Samples cured for 24 hours at room temperature then soaked 30 days in the fluids indicated at 23°C (75°F))

Product Datasheet

Ammonia	Excellent
Vinegar (5% Acetic Acid)	Fair
Hydrochloric Acid (10%)	Fair
Sodium Hydroxide (10%)	Good
Sodium Hydroxide (50%)	Fair
Sulfuric Acid (10%)	Poor
Boric Acid	Excellent
Kerosene	Excellent
Transmission Fluid (Type A & F)	Excellent
Power Steering Fluid	Excellent
Brake Fluid	Fair
Simple Green cleaner (undiluted)	Excellent

Rubbing Alcohol (70% Isopropyl Alcohol & 30% Water)	Fair
Ethanol	Fair
Toluene	Fair
Acetone	Fair
Paint Thinner/Mineral Spirits	Excellent
Turpentine	Good
Chlorinated solvent (carbon tetrachloride)	Fair
Water	Excellent
Mineral Oil	Excellent
Corn Oil	Excellent
Window Washer Fluid	Excellent

Excellent = Recommended for applications requiring long term immersion

Good = Recommended for applications with short term immersion or prolonged minor exposure (such as from spills, vapor, etc.)

Fair = Recommended only for short term spillage or other minor exposure applications

Poor = Not recommend (samples dissolved or dramatically weakened by exposure of more than a few minutes)

PROCESSING AND APPLICATION INSTRUCTIONS

To use, weigh (or proportion by volume) Part A and Part B in the ratio you have selected into a clean mixing container. Mixing containers should preferably be made of polypropylene, polyethylene, glass, or non-corroding metal. (Stainless steel, aluminum, etc.) Always use weighing equipment having accuracy that is $\pm 1\%$ or less of the smallest quantity that you will be weighing. Blend Part A & B thoroughly by using a spatula or stirring stick for at least 2-3 minutes using a kneading motion. Scrape the bottom and sides of the mixing container carefully and frequently to produce a uniform mixture. Vacuum de-gassing after mixing may be helpful for best electrical and physical properties.

Apply to clean, dry surfaces. For best adhesion, abrade the surface with a wire brush, scouring pad, steel wool or coarse sand paper. After abrasion, clean the surface of any loose material and degrease with solvent or detergent to remove any contaminants. The material may then be applied with any suitable application method include brushes, spatulas, trowels, etc.

PACKAGING AVAILABLE

This product is available in a wide range of kits including 1/2-pints, pints, quarts, 1/2-gallons, 1-gallons, 2.5 gallons, 5-gallons, and drums.

It can be supplied in 4oz, 8oz, or 16oz squeeze bottles for easy dispensing of small volumes of material or in dual syringe cartridges in 2:1 or 1:1 by volume mix ratios to eliminate the need for hand mixing.

In addition, pre-mixed and frozen syringes and cartridges are available in a wide variety of sizes (1ml, 3ml, 5ml, 10ml, 20ml, 30ml, 50ml and 55ml syringes, as well as 2.5 oz, 6 oz, and 12 oz cartridges) and styles (manual or air operated, EFD, Techcon, Semco, Iwashita, etc.)

Please call use with any special packaging requests, or for information on custom kitting.

STORAGE GUIDELINES

Store these materials in a clean, cool and dry environment in their tightly closed original containers. Protect from extended exposure to temperatures below 15°C (59°F).

Crystallization may occur if the material is exposed to cold for extend periods. If this occurs, heat the entire container for 4 hours at 60°C to re-liquefy the material. Allow to cool to ambient temperature prior to using. Also protect the EpoPro® 104A&B from exposure to moisture or high humidity. Tightly re-seal containers after use. If the recommended storage conditions are observed the products will have a minimum shelf-life of 12 months from the date of shipment.

HANDLING PRECAUTIONS

Mandatory and recommended industrial hygiene procedures should be followed whenever these products are being handled and processed. For additional information please consult the corresponding material safety data sheets.

PERSONAL HYGIENE

EpoPro® 104A

CAUTION! May cause eye & skin irritation. Prolonged or repeated skin contact or inhalation of vapors may cause allergic skin or respiratory reactions. Harmful if inhaled or swallowed. Avoid contact with eyes, skin, or clothing. Wear eye protection and impervious gloves when handling. Wash thoroughly after handling. Avoid breathing vapor or mist. Keep containers closed when not in use. Use only with adequate ventilation. Do not take internally.

EpoPro® 104B30

WARNING! May cause eye & skin irritation. Prolonged or repeated skin contact or inhalation of vapors may cause allergic skin or respiratory reactions. Harmful if inhaled or swallowed. Avoid contact with eyes, skin, or clothing. Wear eye protection and impervious gloves when handling. Wash thoroughly after handling. Avoid breathing vapor or mist. Keep containers closed when not in use. Use only with adequate ventilation. Do not take internally.

FIRST AID

In case of contact:

Skin – Immediately wash skin thoroughly with mild soap and water. Remove contaminated clothing and wash before reuse. Destroy contaminated shoes and other articles made of leather.

Eyes – Immediately flush eyes with plenty of water for 15 minutes and get prompt medical attention.

Inhalation - Remove person to fresh air. Administer oxygen or artificial respiration if necessary. Call a physician.

Ingestion - Do not induce vomiting. Dilute with plenty of water and contact physician immediately. Never give anything by mouth to an unconscious person.

DISCLAIMER

IMPORTANT: The following supercedes Buyer's documents. **SELLER / MANUFACTURER MAKES NO REPRESENTATION OR WARRANTY, EXPRESS OR IMPLIED, INCLUDING OF**

Product Datasheet



MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. No statements herein are to be construed as inducements to infringe any relevant patent. Under no circumstances shall Seller / Manufacturer be liable for incidental, consequential or indirect damages for alleged negligence, breach of warranty, strict liability, tort or contract arising in connection with the product(s). Buyer's sole remedy and Seller's sole liability for any claims shall be Buyer's purchase price. Data and results presented are based on controlled or laboratory work and must be confirmed by Buyer by testing for its intended conditions of use. The product(s) has not been tested for, and is therefore not recommended for, uses for which prolonged contact with mucous membranes, abraded skin, or blood is intended; or for uses for which implantation within the human body is intended.

Specialty Polymers & Services, Inc. (SP&S)

27822 Fremont Court

Valencia, CA 91355

www.spolymers.com

Tel: 661-294-1790

Fax: 661-294-0640

info@spolymers.com