

EpoPro® 2300 / EpoPro® 215 C

Unfilled, Low Viscosity Epoxy Adhesive, Encapsulating, Impregnating and Laminating System

Typical Properties

(Not for specification purposes. All tests run at 25°C unless otherwise noted)

EpoPro® 2300 Properties:

Appearance	Visual	Pale Yellow, Clear Liquid
Specific Gravity	ASTM D-792	1.14 g/cm ³
Viscosity	ASTM-D-2393	1,800 cP
Flash point, closed cup	ASTM D-92	>200°C (392°F)

EpoPro® 215C Properties:

Appearance	Visual	Light Brown, Clear Liquid
Specific Gravity	ASTM-D-792	0.97 g/cm ³
Viscosity	ASTM-D-2393	3'000 cP
Flash Point, closed cup	ASTM D-92	>194°C (381°F)

Mix Ratio:

Parts by weight (volume) 2A : 1B (2A : 1B)

Mixed Properties:

Initial Viscosity @ 25°C	ASTM-D-2393	2,500cP
Gel time, 100g, @ 25°C		50 minutes

Recommended Cure Schedules:

24 hrs at 25°C **or** 4 hours at 65°C

Please note: any cure schedule selected for use should be confirmed through testing as being appropriate for your particular processing methods and for your intended application.

+

EpoPro® 2300/ EpoPro®215C is a versatile, clear, unfilled, epoxy system. When fully cured this system produces a tough, rigid thermoset polymer that exhibits excellent thermal, mechanical and electrical properties and superior adhesion to most surfaces. This system is designed for either hand or meter-mix processing with a convenient 2:1 mix ratio. It is excellent choice for many encapsulating, potting embedding, sealing and laminating applications.

Suggested Applications:

- Impregnation of wire wound devices, such as coils and small motors
- Sealing of switches and solenoids
- Various adhesive and impregnating applications, including laminating using the hand lay-up technique.

Benefits:

- 2 to 1 mix ratio by weight or volume
- 100% solids (no solvents)
- Low viscosity and Good air release
- Excellent mechanic and dielectric properties

Storage Guidelines:

Store these materials in a clean, dry environment in their tightly closed original container. These products are not considered temperature sensitive, but should ideally be stored at temperatures between 18-30°C (64-86°F). Under these conditions the products will have a minimum shelf-life of 12 months from the date of shipment. If exposed to cold for an extended period crystallization may occur in either the EpoPro 2300 or EpoPro 215C. If lumps or crystals are observed, heat for 2-4 hours at 50 - 60°C to melt the crystals and thoroughly re-mix before using. Do not use while still hot or the work life may be significantly reduced.

Processing Guidelines:

Mix using meter-mix dispensing equipment, or manually, as follows: Weigh the desired amount of resin into mixing container whose weight has been tared. If material has been heated, allow to cool to 25 ± 5°C (77 ± 9°F) before continuing. The pot life of mixed material will be shortened considerably if warm material is used.

Weigh the desired amount of hardener into mixing container with resin. Mix thoroughly by means of a mechanical mixer or manual stirring. Check for uniform color as a sign of complete mixing.

Vacuum deairing is recommended to remove any entrapped air from the mixing procedure. To deair most products, 1-2 minutes under 28 inches of vacuum is recommended for each quart of volume of mixed material. After deairing, quickly dispense potting material into cavity or channel to be sealed.

To reduce the cure time, the parts or casting can be heated. To minimize shrinkage it is recommended to allow the material to gel at room temperature before applying heat to complete the cure. Often, however, small parts or casting (less than 100 grams of EpoPro 2300/EpoPro 215C) can be processed and cured without waiting for the material to gel.

The suitability of immediate heat curing of masses larger than 100 grams will depend on a number of factors

including the amount of EpoPro 215A/B in each part, the temperature being use and the construction of the part. If you are considering using an immediate heat cure, evaluate the results with test parts prior to implementing in production or give SP&S a call so that we can discuss your application and make suggestions on factors to consider. T

In case of humid environments ($\geq 75\%$ relative humidity) it is advisable to complete the cure in an oven at 40-60°C or in a dessicator in order to prevent vapor absorption, leading to steaks on the surface of the casting.

Handling Precautions:

Mandatory and recommended industrial hygiene procedures should be followed whenever these products are being handled and processed. For additional information please consult the corresponding material safety data sheets.

Personal Hygiene:

EpoPro® 2300

Warning! May cause eye irritation. Prolonged or repeated skin contact may cause irritation, and may cause skin reaction. Harmful if inhaled, if swallowed. Avoid contact with eyes, skin, or clothing. Wear eye protection and impervious gloves when handling. Wash thoroughly after handling. Avoid breathing vapor or mist. Keep containers closed when not in use. Use only with adequate ventilation.

EpoPro® 215C

CAUTION! Causes eye, skin, and respiratory irritations. Avoid breathing vapor or mist. Avoid contact with eyes, skin,, and clothing. Keep container closed when not in use. Use with adequate ventilation. Wash thoroughly after handling. In accord with good industrial practice, handle with due care.

First Aid

In case of contact:

Skin - Wash skin thoroughly with mild soap and water. Remove contaminated clothing and wash before reuse. Discard contaminated shoes and other articles made of leather

Eyes - Flush eyes with plenty of water for 15 minutes and get prompt medical attention.

Inhalation - Remove person to fresh air

Ingestion - Do not induce vomiting. Dilute with plenty of water and contact physician immediately. Never give anything by mouth to an unconscious person.

Other- Referral to a physician is recommended if there is any question about the seriousness of an injury.

Disclaimer:

IMPORTANT: The following supercedes Buyer's documents. **SELLER / MANUFACTURER MAKES NO REPRESENTATION OR WARRANTY, EXPRESS OR IMPLIED, INCLUDING OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.** No statements herein are to be construed as inducements to infringe any relevant patent. Under no circumstances shall Seller / Manufacturer be liable for incidental, consequential or indirect damages for alleged negligence, breach of warranty, strict liability, tort or contract arising in connection with the product(s). Buyer's sole remedy and Seller's sole liability for any claims shall be Buyer's purchase price. Data and results presented are based on controlled or laboratory work and must be confirmed by Buyer by testing for its intended conditions of use. The product(s) has not been tested for, and is therefore not recommended for, uses for which prolonged contact with mucous membranes, abraded skin, or blood is intended; or for uses for which implantation within the human body is intended

Specialty Polymers & Services, Inc. (SP&S)
27822 Fremont Court
Valencia, CA 91355

Tel - 661-294-1790

Fax - 661-294-0640

info@spolymers.com

www.spolymers.com