

EpoPro 152 A/B – Preliminary



Two Component, Low viscosity, Transparent Epoxy Adhesive and Impregnation System

Typical Properties

(Not for specification purposes. All tests run at 25°C unless otherwise noted)

EpoPro 152 A Properties:

Appearance	Visual	Clear Liquid
Specific Gravity	ASTM-D-2393	1.18 g/cc
Viscosity at 25°C	ASTM-D-792	1,200 cP
Flash Point, closed cup	ASTM-D-92	> 140°C (> 284°F)

EpoPro 152 B Properties:

Appearance	Visual	Clear Liquid
Specific Gravity	ASTM-D-2393	0.94 g/cc
Viscosity at 25°C	ASTM-D-792	50 cP
Flash Point, closed cup	ASTM-D-92	> 110°C (>230°F)

Mix Ratio:

Parts by weight (volume) 100A : 38B* (100A:47B)

* 100A:38B is the standard mix ratio – the use of small amounts of additional hardener will shorten the pot life of the system.

Mixed Properties:

Initial Viscosity, 100g c	ASTM-D-792	525 cP
Gel Time (70 g mass)	Gardner	63 minutes
Pot life (100 ml. mass)	OC-WI-001	60 minutes

Recommended Cure Schedules:

7 days at 25°C or 24 hours at 25°C + 4 hours at 100°C.

Please note: any cure schedule selected for use should be confirmed through testing as being appropriate for your particular processing methods and for your intended application.

Cured Properties (cured 24h @ 25°C + 4h 110°C)

Appearance	Visual	Clear, Light Yellow
Cured Density	ASTM-D-792	1.11 g/cc
Shore Hardness	ASTM-D-2240	87D
Coefficient of Thermal Expansion(CTE) (per °C)	ASTM-E-831	65 x 10 ⁻⁶
Glass Transition Temp. (T _g)	ASTM-E-1545	120°C (248°F)
Heat Deflection Temp.		110°C (230°F)
Thermal Conductivity	ASTM D-2214	0.00068 cal/cm-sec-°C or 0.28 W/mK

EpoPro 152 A/B is a two part, cold curing epoxy adhesive and laminating system that contains no solvents, but when mixed provides a very low viscosity. Ambient cure of this system will result in glass-transition temperatures (T_g) of about 60°C, which can be increased to a maximum of about 130°C by post-curing the parts at 100°C. It has exceptional air release properties that reduces the likelihood for air entrapment in the cured material and increases the reliability of the encapsulated components or laminated substrates. It is recommended for adhesive bonding of transparent substrates or where invisible bond-lines are desired as it is quite transparent.

It is also recommended for the encapsulation of closely spaced components or tightly wound coils due to its excellent wetting and flow characteristics. It is especially useful in encapsulant applications where visual inspection is desired.

Benefits:

- Low viscosity and excellent impregnation or tightly spaced or wire wound devices
- Long pot-life resulting in long processing times
- Tough polymer with excellent high temperature resistance.
- Excellent bond strength to metals & ceramics and good bonds to many plastics including epoxies, polystyrene, polysulfone, polycarbonate, rigid PVC & PVDC
- Excellent mechanical and dynamic properties after ambient curing, with possible increases of these properties after curing at elevated temperatures.

Suggested Processing Guidelines:

To prepare the system for use, weigh Part A and Part B in the recommended ratio as accurately as possible into a clean mixing container. Always use weighing equipment having accuracy in proportion to the amounts being weighted. (preferably with an accuracy that is 0.5% or less of the quantity being weighed out.)

If mixing by hand, blend by using a spatula or stirring stick for 2-3 minutes using a kneading motion. Scrape the bottom and sides of the mixing container carefully and frequently to produce a uniform mixture.

For adhesive applications, apply the mixed material to all surfaces to be bonded & then join together using a clamp or other methods to hold the surfaces in place until the adhesive is set. Only contact pressure is required - do not use excessive clamping pressure as this may squeeze the adhesive out of the bond-line.

For encapsulating applications, pour or dispense the fully mixed material into the components to be encapsulated.

If not using vacuum, pour the fully mixed system into the device in a one continuous thin stream and allow the material to flow through the device and force out any air as the material level increases.

For laminating and tooling applications, the material can be applied using wet lay-up, resin transfer molding (RTM), pressure molding and filament winding techniques.

Once the material is applied as desired, allow the system to cure as indicated in the recommended cure schedules. Please note that when using a heat cure it is often advisable to first allow the epoxy to gel at room temperature prior to heat curing. This step will minimize shrinkage during curing and reduce the possibility of thermally induced stress or cracking. Also please note that many custom cure schedules are possible. If you are interested in using a modified cure schedule please contact SP&S and we will make recommendations suitable for your specific application.

Storage Guidelines:

Store these materials in a clean, cool and dry environment in its tightly closed original container. The products may crystallize during storage if subject to cold. If crystallization is observed (increased viscosity, haziness, or the appearance of crystals), the products may be reliquified by warming the contents of the shipping containers, loosely covered, to 65°C for 2-4 hours. Allow contents to slowly cool to room temperature prior to use. Avoid extended exposure to extreme humidity. If the recommended storage conditions are observed the products will have a minimum shelf-life of 12 months from the date of shipment.

Handling Precautions:

Mandatory and recommended industrial hygiene procedures should be followed whenever these products are being handled and processed. For additional information please consult the corresponding material safety data sheets.

Exotherm Warning: when large masses of epoxy compounds such as EpoPro 152 A/B are mixed they may generate excessive heat if allowed to remain in a large mass for an extended period. Take care when mixing quantities large than 500g (~ 1.1 lbs.) to use the material as quickly as possible or to divide the material into smaller containers or to spread the material out into thin sections so that the heat generated by the reacting material does not create a catastrophic exotherm. Contact SP&S to discuss your application and ways to minimize exotherm if any excessive heat is observed or if you are working with large mixes of this system.

Personal Hygiene:

EpoPro 152A

WARNING!!! Causes severe eye irritation. Causes skin irritation and possible allergic skin reaction.

Harmful if inhaled. Harmful if swallowed. Avoid contact with eyes, skin, or clothing. Wear eye protection and impervious gloves when handling. Wash thoroughly after handling. Avoid breathing vapor or mist. Keep containers closed when not in use. Use only with adequate ventilation. Do not take internally.

EpoPro 152B

WARNING! CORROSIVE! Causes severe eye and skin burns and possible allergic skin reaction. Vapor irritating to eyes, skin and nasal mucous membranes. Harmful if swallowed. Do NOT get in eyes, on skin, or clothing. Wear chemical splash goggles and impervious gloves when handling. Wash skin and clothing thoroughly after handling. Avoid breathing vapor or mist. Use only with adequate ventilation. Keep containers closed when not in use. Do NOT take internally.

First Aid

In case of contact:

Skin – Immediately wash skin thoroughly with mild soap and water. Remove contaminated clothing and wash before reuse. Destroy contaminated shoes and other articles made of leather.

Eyes – Immediately flush eyes with plenty of water for 15 minutes and get prompt medical attention.

Inhalation - Remove person to fresh air. Administer oxygen or artificial respiration if necessary. Call a physician.

Ingestion - Do not induce vomiting. Dilute with plenty of water and contact physician immediately. Never give anything by mouth to an unconscious person.

Disclaimer:

IMPORTANT: The following supercedes Buyer's documents. **SELLER / MANUFACTURER MAKES NO REPRESENTATION OR WARRANTY, EXPRESS OR IMPLIED, INCLUDING OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.** No statements herein are to be construed as inducements to infringe any relevant patent. Under no circumstances shall Seller / Manufacturer be liable for incidental, consequential or indirect damages for alleged negligence, breach of warranty, strict liability, tort or contract arising in connection with the product(s). Buyer's sole remedy and Seller's sole liability for any claims shall be Buyer's purchase price. Data and results presented are based on controlled or laboratory work and must be confirmed by Buyer by testing for its intended conditions of use. The product(s) has not been tested for, and is therefore not recommended for, uses for which prolonged contact with mucous membranes, abraded skin, or blood is intended; or for uses for which implantation within the human body is intended

Specialty Polymers & Services, Inc. (SP&S)
27822 Fremont Court
Valencia, CA 91355

Tel - 661-294-1790
Fax - 661-294-0640

info@spolymers.com
www.spolymers.com