

Advanced Materials**RenLam[®] 4014 / Ren[®] 1500 Laminating System****HEAT RESISTANT EPOXY LAMINATING SYSTEM**

- High Temperature Performance
- Good Work Life

DESCRIPTION :

RenLam[®] 4014 (Resin) / Ren[®] 1500 (Hardener) laminating system is a gray, filled, two-component material intended for use when heat resistance is required. RenLam[®] 4014 / Ren[®] 1500 laminating system is suited for continual use at temperatures ranging from 77°F (25°C) to 300°F (149°C) after an elevated temperature postcure. Intermittent use is possible in the 300°F (149°C) to 350°F (177°C) range. Laminated tools built with the system can be constructed with regular hand lay-up techniques or vacuum bagged if the tool is small enough to allow the operator to complete bagging and squeezing operations before the material starts to gel. RenLam[®] 4014 / Ren[®] 1500 epoxy laminating system is well suited for use in building vacuum-form and compression molds as well as other high-temperature tooling. The epoxy can be utilized with large quantities of bulk fill such as RP 39 aluminum grain for casting.

TYPICAL PROPERTIES*

<u>Property</u>	<u>Test Values</u> ⁽¹⁾	<u>Test Method</u>
Color, RenLam [®] 4014	Gray	Visual
Ren [®] 1500	Amber	
Mixed	Gray	
Viscosity, mixed, cP at 77°F (25°C)	4,000	ASTM-D-2393
Gel time, 4 fl. oz. at 77°F (25°C), min.	55	ASTM-D-2471

⁽¹⁾Tested at 77°F (25°C)

MIX RATIO :

RenLam[®] 4014 : Ren[®] 1500
100:11 by weight
100:14 by volume

Stir each component thoroughly before use. Weight each component accurately ($\pm 5\%$) into clean containers. Thoroughly mix resin and hardener together (minimum of three minutes), scraping container sidewalls, bottom and mixing stick several times to assure a uniform mix.

TYPICAL CURED PROPERTIES :

	<u>Cure Value</u>	<u>Test-Method</u>
Specific Gravity (cast)	1.34	ASTM D-792
Cubic Inch per Pound	20.8	ASTM D-792
Hardness, Shore D	90	ASTM-D-2240
Ultimate Flexural Strength, psi (MPa)		ASTM-D-790
at 77°F (25°C)	34,000 (234)	
at 300°F (149°C)	13,000 (89.6)	
at 77°F (25°C) after 400 hrs. at 350°F (177°C)	35,600 (246)	
at 300°F (149°C) after 400 hrs. at 350°F (177°C)	10,000 (69)	
Flexural Modulus, psi (MPa)		ASTM-D-790
at 77°F (25°C)	1.7x10 ⁶ (11,724)	
at 300°F (149°C)	0.8x10 ⁶ (5,517)	
at 77°F (25°C) after 400 hrs. at 350°F (177°C)	1.5x10 ⁶ (10,345)	
at 300°F (149°C) after 400 hrs. at 350°F (177°C)	0.6x10 ⁶ (4,138)	
Ultimate Tensile Strength, at 77°F (25°C), psi (MPa)	24,000 (166)	ASTM D-638
Tg by DMA, E'', °F (°C)	333 (167)	ASTM D-4065
Ultimate Compressive Strength, at 77°F (25°C), psi (MPa)	28,000 (193)	ASTM D-695
Coefficient of Thermal Expansion, in./in./°F	1.4 x 10 ⁻⁶	ASTM D-3386

Cure Schedule – Contact laminate, 10 oz. glass cloth, 90° rotation, postcured 24 hrs. at 77°F (25°C), + 2 hrs. at 150°F (66°C) + 2 hrs. 200°F (93°C) + 2 hrs. at 250°F (121°C) + 2 hrs. at 300°F (149°C), tested at 77°F (25°C).

NOTE : Typical Properties – These physical properties are reported as typical test values obtained by our test laboratory. If assistance is needed in establishing product specifications, please consult with our Quality Control Department.

CURING INSTRUCTIONS :

With proper backup completed, allow to gel at room temperature followed by a postcure of two hours at 150°F (66°C) plus two hours at 200°F (93°C), plus two hours at 250°F (121°C), plus two hours at 300°F (149°C).

HANDLING:

Material temperatures should be about 65°F (18°C) when mixing. After use, tightly reseal containers.

STORAGE :

RenLam® 4014 / Ren® 1500 should be stored in a dry place, in the sealed original container, at temperatures between +2°C and +40°C (+35.6°F and 104°F). Under these storage conditions, the shelf life is 2 years. The product should not be exposed to direct sunlight.

PRECAUTIONARY STATEMENT :

Huntsman Advanced Materials Americas LLC maintains up-to-date Material Safety Data Sheets (MSDS) on all of its products. These sheets contain pertinent information that you may need to protect your employees and customers against any known health or safety hazards associated with our products. Users should review the latest MSDS to determine possible health hazards and appropriate precautions to implement prior to using this material.

First Aid!

Refer to MSDS as mentioned above.

KEEP OUT OF REACH OF CHILDREN**FOR PROFESSIONAL AND INDUSTRIAL USE ONLY**

IMPORTANT LEGAL NOTICE

Sales of the product described herein ("Product") are subject to the general terms and conditions of sale of either Huntsman Advanced Materials LLC, or its appropriate affiliate including without limitation Huntsman Advanced Materials (Europe) BVBA, Huntsman Advanced Materials Americas Inc., or Huntsman Advanced Materials (Hong Kong) Ltd. ("Huntsman"). The following supercedes Buyer's documents.

Huntsman warrants that at the time and place of delivery all Products sold to Buyer shall conform to the specifications provided to Buyer by Huntsman.

While the information and recommendations included in this publication are, to the best of Huntsman's knowledge, accurate as of the date of publication, NOTHING CONTAINED HEREIN (EXCEPT AS SET FORTH ABOVE REGARDING CONFORMANCE WITH SPECIFICATIONS PROVIDED TO BUYER BY HUNTSMAN) IS TO BE CONSTRUED AS A REPRESENTATION OR WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, NONINFRINGEMENT OF ANY INTELLECTUAL PROPERTY RIGHTS, OR WARRANTIES AS TO QUALITY OR CORRESPONDENCE WITH PRIOR DESCRIPTION OR SAMPLE, AND THE BUYER ASSUMES ALL RISK AND LIABILITY WHATSOEVER RESULTING FROM THE USE OF SUCH PRODUCT, WHETHER USED SINGLY OR IN COMBINATION WITH OTHER SUBSTANCES.

No statements or recommendations made herein are to be construed as a representation about the suitability of any Product for the particular application of Buyer or user or as an inducement to infringe any patent or other intellectual property right. Buyer is responsible to determine the applicability of such information and recommendations and the suitability of any Product for its own particular purpose, and to ensure that its intended use of the Product does not infringe any intellectual property rights.

The Product may be or become hazardous. The Buyer should obtain Material Safety Data Sheets and Technical Data Sheets from Huntsman containing detailed information on Product hazards and toxicity, together with proper shipping, handling and storage procedures for the Product, and should comply with all applicable governmental laws, regulations and standards relating to the handling, use, storage, distribution and disposal of, and exposure to the Product. Buyer shall also take all steps necessary to adequately inform, warn and familiarize its employees, agents, direct and indirect customers and contractors who may handle or be exposed to the Product of all hazards pertaining to and proper procedures for safe handling, use, storage, transportation and disposal of and exposure to the Product, and the containers or equipment in which the Product may be handled, shipped or stored.

Ren and RenLam are registered trademarks of Huntsman LLC or an affiliate thereof in one or more countries, but not all countries.

© 2010 Huntsman Advanced Materials Americas Inc.

Main Offices :
Huntsman Corporation
10003 Woodloch Forest Dr.
The Woodlands
Texas 77380
(281) 719-6000

**Huntsman Advanced Technology
Center**
8600 Gosling Rd.
The Woodlands
Texas 77381
(281) 719-7400