

SilPro™ 305

One Component, Non-Slumping/Non-Sagging Silicone Adhesive & Sealant

Product Description

SilPro 305 is a one component, medium modulus, silicone that cures at room temperature when exposed to atmospheric moisture. This material has a low VOC content and a neutral curing mechanism that makes it ideal for electronics and other corrosion sensitive applications. The cured silicone rubber offers UV stability, fungus and mildew resistance, and tenacious adhesion to most materials including pvc, concrete, glass, aluminum, steel, painted surfaces, wood, brick, stone, and many rigid plastics. The cured silicone rubber exhibits excellent resistance to outdoor weathering in all weather conditions and meets today's Green Building Standards

SilPro 305 is available in a standard black color and is also available in clear, white, gray, tan and many custom colors by request. It is ideal for many industrial & electronic gasket & sealing applications, for marine applications, for construction and appliance applications, and for HVAC, refrigeration, roofing, & plumbing applications.

Key Features

- Will not shrink or crack
- Temperature Resistant from -62°F to +350°F (-52°C to 177°C)
- Superior Joint Movement (± 25%)
- RoHS and REACH Compliant

Typical Properties

UNCURED PROPERTIES	
Appearance	Black, Gray, Clear, White, Tan, or custom color
Viscosity	Thixotropic Paste
Extrusion Rate, 1/8" orifice at 50 psi	200 grams / minute
Specific Gravity	1.35
Volatile Organic Content	40 grams / liter
Skin Over Time at 25°C*	15 minutes
Tack Over Time at 25°C *	25 minutes
Cure Rate at 25°C & 50% Relative humidity	1/8" per 30 hours
Full Cure:	1- days at room temperature and with an ambient humidity of 30% - 80%. Sections thicker than 1/2" may take longer to cure.
Alternate Cure:	4-8 hours at 60°C in an oven with moisture vapor lines or a dish of water to provide humidity.

*Curing tested at 25C and 50% relative humidity in a 1/8" thickness. Ambient temperature, humidity levels, and product thickness will affect the cure rate.

CURED PROPERTIES:	
Tensile Strength	310 psi
Tensile Elongation	410%
Shore A Hardness	35A
Movement capability	± 25%
Dielectric Strength	500 Volts/mil

Dielectric Constant at 100 Hz	2.7 kHz
Dissipation Factor	0.0015
Volume Resistivity	1 x 10 ¹⁴ ohm-cm
Temperature Range of Use, continuous or cyclical	-62°F to +350°F (-52°C to 177°C)
Maximum Short Term Temperature Limit	400°F (204°C)

Note: Not for Product Specification Purposes – these are typical values and based on 7 days curing with approximately 50% relative humidity. Please contact SP&S for assistance in writing purchasing specifications.

Curing Characteristics

Under normal room temperature conditions (23°C - 27°C) and humidity (30% - 80% relative humidity) and in a thickness of 1/8" or less, the SilPro 305 will develop a skin in about 15 minutes and cure to approximately 90% of its final strength in 18 – 24 hours. Full strength will develop in 1 – 2 days. Because this adhesive cures with exposure to moisture and under ambient temperature conditions, a change in curing speed may be seen if the temperature or humidity changes.

Application:

SilPro 305 is typically applied directly from its original tube, syringe, or cartridge. Once dispensed it may be spread using a spatula or other tools to achieve the desired bond line or seal. For most surfaces, including most metal, plastics, glass, and rubbers, priming will not be necessary. However, if insufficient bond strength is observed or curing inhibition is witnessed a primer such as our Primax SF may be useful to prime and seal the surface prior to application of the SilPro 305.

Please note that the SilPro 305 is generally not suitable for bonding calcareous surfaces (i.e. those containing calcium carbonate, chalk, or limestone) primers may be possible for some surfaces, but will require evaluation to determine suitability for each surface and application. The SilPro 305, and many other adhesives, will also find it difficult to bond to surfaces that bleed oils, plasticizers, or solvents as these can prevent adhesion to the surfaces. Finally, please note that the cured SilPro 305 is generally not paintable and is not intended as an adhesive for the structural bonding of mirrors.

Shelf-life and Storage

SilPro 305 should be stored in their original, sealed containers in an environment that does not exceed 38°C (100°F). Under these conditions the expected shelf-life of the material is a minimum of 12 months from Date of Shipment. Storage at 4°C – 8°C, in the tightly closed original containers, may prolong the shelf-life to 18 months or longer.

FIRST AID

In case of contact:

Skin – Immediately wash skin thoroughly with mild soap and water. Remove contaminated clothing and wash before reuse. Destroy contaminated shoes and other articles made of leather.

Eyes – Immediately flush eyes with plenty of water for 15 minutes and get prompt medical attention.

Inhalation - Remove person to fresh air. Administer oxygen or artificial respiration if necessary. Call a physician.

Ingestion - Do not induce vomiting. Dilute with plenty of water and contact physician immediately. Never give anything by mouth to an unconscious person.

DISCLAIMER:

IMPORTANT: The following supercedes Buyer's documents. **SELLER / MANUFACTURER MAKES NO REPRESENTATION OR WARRANTY, EXPRESS OR IMPLIED, INCLUDING OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.** No statements herein are to be construed as inducements to infringe any relevant patent. Under no circumstances shall Seller / Manufacturer be liable for incidental, consequential or indirect damages for alleged negligence, breach of warranty, strict liability, tort or contract arising in connection with the product(s). Buyer's sole remedy and Seller's sole liability for any claims shall be Buyer's purchase price. Data and results presented are based on controlled or laboratory work and must be confirmed by Buyer by testing for its intended conditions of use. The product(s) has not been tested for, and is therefore not recommended for, uses for which prolonged contact with mucous membranes, abraded skin, or blood is intended; or for uses for which implantation within the human body is intended

Specialty Polymers & Services, Inc. (SP&S)

27822 Fremont

Valencia, CA 91355

www.spolymers.com

Tel: 661-294-1790

Fax : 661-294-0640

info@spolymers.com