

Product Information

Liquid Silicone Rubber

DOW CORNING

SILASTIC® 9252/500P

FEATURES

- Good clarity
- Easily pigmentable
- Formulated to meet BgVV, XV and FDA 21 CFR 177.2600
- Unprimed adhesion to glass fabric

40 Durometer, two-part, 1 to 1 mix, translucent, fabric coating grade Liquid Silicone Rubber

APPLICATIONS

- Fabric coating
- Electrical-wire sleeving
- Suitable for food contact

TYPICAL PROPERTIES

Specification writers: These values are not intended for use in preparing specifications. Please contact your local Dow Corning sales representative prior to writing specifications on this product.

Test Method ¹	Property	Unit	Value
	As supplied		
	Solids content	%	100
	Mixed viscosity	mPa.s	64,000
	As molded		
D792	Specific gravity		1.11
D2240	Hardness	Shore A	36
D412 DIE C	Tensile strength	MPa (psi)	6.0 (870)
D412 DIE C	Elongation at break	%	460
D624 DIE B	Tear strength	kN/m (ppi)	10 (57)
D257	Volume resistivity	Ohm.cm	2.0x10 ¹⁵

1. Properties obtained on 2mm thick slabs: Press cured 10 minutes at 120°C (248°F).

ASTM: American Society for Testing and Materials.

Materials were tested according to Dow Corning Corporate Test Methods (CTM), which in most cases are similar to the ASTM standard listed above. Copies of CTMs are available on request.

Viscosity measured on the Brookfield HAF Viscometer, spindle 7, 10 r.p.m.

HOW TO USE

Mixing and de-airing

The A and B components are supplied strained and de-aired to be used as lot matched kits.

Mix parts A and B in a 1:1 ratio. Meter mix equipment which pumps, meters and mixes the two components without the incorporation of air is strongly recommended for production. If air bubbles are entrapped during mixing the mixture must be thoroughly de-gassed under vacuum.

Pot life

When parts A and B are mixed the mixture will remain usable for 72 hours at 25°C (77°F).

Cleaning

The uncured silicone can readily be removed by most hydrocarbon solvents. Polar solvents, such as ketones and alcohols, are not suitable.

Curing

SILASTIC 9252/500P cures rapidly at elevated temperatures. A 2mm cross-section requires 8-14 seconds at 200°C (392°F). The cure time depends on the thickness and the cure temperature used. Cure can be inhibited by contact with certain materials such as amines, sulphur and tin complexes.

Pigmentation

This is normally carried out during mixing and dispensing of the two components. SILASTIC LPX Liquid Color Master batches are recommended with normal addition levels of 2 to 4% based on total volume. These are available from Dow Corning.

HANDLING PRECAUTIONS

Product safety information required for safe use is not included. Before handling, read product and safety data sheets and container labels for safe use, physical and health hazard information. The material safety data sheet is available on the Dow Corning website at www.dowcorning.com. You can also obtain a copy from your local Dow Corning sales representative or Distributor or by calling your local Dow Corning Global Connection.

USABLE LIFE AND STORAGE

When stored at or below 32°C (90°F) in the original unopened containers, this product has a usable life of 15 months from the date of production.

PACKAGING

This product is supplied in lot matched kits: in pails (20kg and 20kg) and in drums (205kg and 205kg).

FOOD CONTACT

This product has been formulated to meet applicable food contact regulations and recommendations (for example: FDA 21.CFR 177.2600 and BgVV, XV). For further details on the suitability of this product for food contact applications, please refer to the Food Regulatory Profile. This information is available from your local Dow Corning Customer Service Center.

Post cure is recommended to ensure that food contact requirements are met.

Note: It remains the manufacturers' responsibility to test the final product.

LIMITATIONS

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

HEALTH AND ENVIRONMENTAL INFORMATION

To support Customers in their product safety needs, Dow Corning has an extensive Product Stewardship organization and a team of Product Safety and Regulatory Compliance (PS&RC) specialists available in each area.

For further information, please see our website, www.dowcorning.com or consult your local Dow Corning representative.

CONTACT INFORMATION

For further help or assistance see our website on www.dowcorning.com or contact:

Europe

Germany, Austria, Switzerland & Eastern Europe
Dow Corning GmbH
Germany
Tel.: +49 (0) 611 - 237 774
Fax: +49 (0) 611 - 237 610

France & North Africa
Dow Corning S.A.
France
Tel.: +33 (0) 4 72 84 13 60
Fax: +33 (0) 4 72 84 13 79

Italy & Eastern Mediterranean Countries
Dow Corning S.p.A.
Italy
Tel.: +39 02 98 832 1
Fax: +39 02 98 804 83

United Kingdom, Eire, Nordic Countries, Benelux, South Africa & Middle East
Dow Corning Ltd.
United Kingdom
Tel.: +44 (0) 1 676 52 80 00
Fax: +44 (0) 1 676 52 80 01

Spain & Portugal
Dow Corning Ibérica S.A.
Spain
Tel.: +34 93 36 36 900
Fax: +34 93 36 36 901

Americas

Dow Corning Corp
111 S. Progress Dr. E.
Kendallville, IN 46755
Tel.: 260-347-5813
Fax: 260-347-5819

**LIMITED WARRANTY
INFORMATION - PLEASE
READ CAREFULLY**

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customers' tests to ensure that Dow Corning's products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

Dow Corning's sole warranty is that the product will meet the Dow Corning sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.

**DOW CORNING SPECIFICALLY
DISCLAIMS ANY OTHER
EXPRESS OR IMPLIED
WARRANTY OF FITNESS FOR
A PARTICULAR PURPOSE OR
MERCHANTABILITY.**

**DOW CORNING DISCLAIMS
LIABILITY FOR ANY
INCIDENTAL OR
CONSEQUENTIAL DAMAGES.**

We help you invent the future.™

www.dowcorning.com

