

Product Type

Pumpable, high temperature sealant, heat curing, PVC free, polyacrylate plastisol based

Substrate Type

Electrocoat or clean bare steel

Application

Clean metal or electrocoat prior to powder coat

Product Technology

TEROSON AL 6302 (known as TEROSOL 6302) is a heat curing, solvent free sealant based on a polyacrylic plastisol. It can be applied to clean, bare steel or electrocoat and accepts powder paint either cured or wet on wet.

TEROSON AL 6302 (known as TEROSOL 6302) is used in high heat applications (200°C) where resistance to heat degradation and color change is important.

Typical Properties

Property	Typical Results
Color	White
Odor	Slight, mild
Solids	>99%
Specific Gravity	1.45 ± 0.05
Severs Viscosity 0.104" orifice, 40 psi, 25°C – s/20g	7 – 20 s/20g
Adhesion to Ecoat and bare steel 30 minutes @ 175°F	Excellent
Heat Resistance 1 hour @ 200°C	Excellent
Application Temperature	15°C – 25°C

Operating Summary

- It is recommended that testing is completed on substrates to be used to validate this material prior to use.
- Deviations from cure cycle may result in deviations from the shear strength which may interfere with material performance.

General Information

- Shutdown** - For extended shutdown periods, greater than 8 hours, it is recommended that pressure be removed from the system to reduce possibility of caking in lines.
- Material Purge** - Regular purge and cleaning of the application system is recommended, please contact your sales representative for material requirements and instructions.
- As with all materials, it is recommended that to ensure consistent material, this product is used in a First In - First Out

Equipment

- TEROSON AL 6302 (known as TEROSOL 6302) can be applied with standard piston, gear or rotary pumps. It can also be applied out of cartridge tubes.
- The material is homogeneous and contains no abrasives that will affect pumping equipment.
- This material can be dispensed using a pumping system. This should include a high pressure ratio pump, with a follower plate and flow guns with tips appropriate to the bead size needed. Care should be taken in system design to insure that flow restrictions are minimized. Flow restrictions occur when headers, hoses, and/or nozzles are too small for the application.

Metal Surface Preparation

- This material has been developed to adhere to metals which have been cleaned, treated, and primed.
- This material will not adhere to untreated metal.
- For best performance, substrate should be free of contamination before material is applied.

Product Removal

- Fresh, uncured material can be removed with the aid of Isopropyl Alcohol. Large amounts of material can be removed using towels or rags and then cleaned with Isopropyl Alcohol.
- Cured material can only be removed mechanically

Health and Safety

- For safe handling information on this product, consult the Material Safety Data Sheet (MSDS).**
- Prior to application it is necessary to read the Safety Data Sheet for information about precautionary measures and safety recommendations.
- For chemicals exempt from compulsory labeling, the relevant precautions should always be observed.

Product Control Test Method

- No specific test methods are recommended to be used by customer.
- Additional information on product testing is available upon request.

stock rotation system.

Storage Requirements

- Store product in the unopened container in a dry location
- **Keep away from heat and direct sunlight.**
- **Store between 5°C and 25°C (41°F and 77°F)**
- **Material is frost sensitive.**
- **Shelf life of product is 365 days.**
- Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Waste Disposal

- Refer to MSDS for further information

Order Information

- Bulk IDH Number **882425**
- Please call for available packaging

Creation Date 13 March 2006

13 February

Revision Date 2014 **Revision Number** 3

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$

mm / 25.4 = inches

$\mu\text{m} / 25.4 = \text{mil}$

N x 0.225 = lb

N/mm x 5.71 = lb/in

N/mm² x 145 = psi

MPa x 145 = psi

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

REVISION HISTORY

- | | |
|----------|--|
| 03.13.09 | New format |
| 05.23.13 | Updated storage conditions and temperatures.
Updated name due to rebranding. Updated Typical Properties table |
| 02.13.14 | Updated storage temps and shelf life from 90 to 365 days |