

## Ultralane<sup>®</sup> 753-4A/B



### SHORE 97A / 52D POLYURETHANE CASTING SYSTEM

Ultralane<sup>®</sup> 753-4A/B is harder and more abrasion resistant version of our standard Ultralane<sup>®</sup> 753A/B system. It is an easy to use, low viscosity casting system that readily picks up mold details and releases air bubbles. It contains no MOCA or TDI, but still develops high tensile strength and tear strengths without a heat cure. It is excellent for casting resilient, abrasion resistant parts and pads. It is also excellent for electrical encapsulation of stress-sensitive components and is helpful in protecting against vibration.

The Ultralane 753-4 system is available in a natural tan color or in a pigmented black coloration. Natural color is easy to pigment or dye prior to curing to achieve a wide range of colors and visual effects. Custom colored versions are also available by request, as are versions containing UV stabilizers or anti-oxidants that can provide extra protection against extended exposure to UV light or high temperatures during use. Other custom variations are possible, please contact us to discuss the development of a custom variant that would be suitable for your application.

#### SUGGESTED APPLICATIONS:

- Prototype & Short-run parts
- Ideal for metal-forming applications and parts such as impellers, rollers, gears and wheels.
- Electric Encapsulation and Bonding applications

<b>HANDLING PROPERTIES</b>	<b>VALUE</b>	<b>TEST METHOD</b>
<u>Ultralane 753-4A (resin)</u>		
Visual Appearance	Dark amber to Brown liquid	
Density, Part A	1.2 g/cm <sup>3</sup>	ASTM E-201
Viscosity, Part A, @ 25°C	150 cps	ASTM D-2393
Flash Point	>93°C	ASTM D-92
<u>Ultralane 753-4B (hardener)</u>		
Visual Appearance	Milky-white or Black Liquid	
Density,	1.07 g/cm <sup>3</sup>	ASTM E-201
Viscosity, Part B, @ 25°C	1,100 – 1,500 cps	ASTM D-2393
Flash Point	>93°C	ASTM D-92
Mixed Viscosity @ 25°C	800 cps	ASTM D-2393
Mix Ratio by weight and volume:	1A : 2B by weight or volume	
Pot life, 4oz / 150 gram mass	20 - 35 minutes	
Demolding time:	4-8 hours @ room temperature or allow to gel then cure for 2 hours at 150°F or 1 hour @ 80°C. Allow it to cool prior to demolding.	
Cure Schedules:	24 hours at 25°C (Full properties may take up to 7 days at room temperature) <b>or</b> gel at 25°C for at least 2 hours + 4-8 hours at 80°C.	

# Product Datasheet



<b>CURED PROPERTIES</b>	<b>ROOM TEMP. CURE</b>	<b>HEAT CURE</b>	<b>TEST METHOD</b>
Density	69 lb./ft <sup>3</sup> (1.1 g/cm <sup>3</sup> )	69 lb./ft <sup>3</sup> (1.1 g/cm <sup>3</sup> )	ASTM D-792
Hardness, Shore D at 25°C(77°F)	52	54	ASTM D-2240
Hardness, Shore A			
at 25°C (77°F)	97	99	ASTM D-2240
at 65°C (150°F)	94	95	
at 80°C (175°F)	94	95	
at 93°C (200°F)	94	95	
at 121°C (250°F)	89	90	
at 138°C (280°F)	72	76	
at 150°C (300°F)	48	48	
After cycling to 150°C, cooled then re-testing at 25°C	98	98	
Ultimate Tensile Strength	2,680 psi	3,540 psi	ASTM D-638
Tensile Elongation	220%	360%	ASTM D-638
Tear Strength	478 ppi	580 ppi	ASTM D-624
Compressive Set	64%	27%	ASTM D-395B
Linear Shrinkage during cure*	0.001 in/in	0.004 in/in	ASTM D-624
Coefficient of Thermal Expansion			ASTM E-381
(-30°C to +30°C)	169 ppm/°C	-	
(0°C to 80°C)	191 ppm/°C	-	
Water Absorption by weight			ASTM D-570
24 hrs. at 25°C	1.1%	-	
7 days at 25°C	2.12%	-	
2 hours in boiling water	2.58%	-	
Thermal conductivity	0.2 W/mK	0.2 W/mK	ASTM D-2214

\* Molds are half round steel, 10 inches long, 0.875 inches deep

## **PROCESSING AND APPLICATION INSTRUCTIONS :**

The Ultralane 753-4B component may settle during storage or transportation. Shaking or stirring the container of 753-4B prior to use will ensure that the material is uniform.

To use, weigh Part A and Part B into a clean mixing container. Mixing containers should preferably be made of polypropylene, polyethylene, glass, or non-corroding metal such as stainless steel or aluminum. Always use weighing equipment having accuracy that is  $\pm 1\%$  or less of the smallest quantity that you will be weighing. Blend Parts A & B thoroughly using a spatula or stirring stick for at least 2 minutes using a kneading motion. Scrape the bottom and sides of the mixing container carefully and frequently to produce a uniform mixture.

## **PACKAGING AVAILABLE:**

This product is available in 5-gallon pails. It can also be supplied in 1-gallon, quarts, and other size containers.

Please call use with any special packaging requests or for information on custom kitting.

## **STORAGE GUIDELINES:**

Store these materials in a clean, cool and dry environment in their tightly closed original containers. Protect from extended exposure to temperatures below 15°C (59°F). Crystallization may occur if the material is exposed to cold for extended periods. If this occurs, heat the entire container for 4 hours at 70°C to re-liquify the material. Allow to cool to ambient temperature prior to using. Also protect the EpoPro 104A&B from exposure to moisture or high humidity. Tightly re-seal containers after use. If the recommended storage conditions are observed the products will have a minimum shelf-life of 12 months from the date of shipment.

## **HANDLING PRECAUTIONS & PERSONAL HYGIENE**

Mandatory and recommended industrial hygiene procedures should be followed whenever these products are being handled and processed. For additional information please consult the corresponding material safety data sheets.

### **Ultralane 753-4A**

**WARNING!** Can cause skin irritation, eye irritation, allergic respiratory reaction, and allergic skin reaction. Can be Harmful if inhaled. May cause eye & skin irritation. Avoid contact with eyes, skin, or clothing. Wear eye protection and impervious gloves when handling. Wash thoroughly after handling. Avoid breathing vapor or mist. Keep containers closed when not in use. Use only with adequate ventilation. Do not take internally.

### **Ultralane 753-4B**

**WARNING!** In accord with good industrial practice, handle with due care. Could cause eye, skin, and respiratory irritation. Prolonged or repeated skin contact or inhalation of vapors may cause allergic skin or respiratory reactions. Harmful if inhaled or swallowed. Avoid contact with eyes, skin, or clothing. Wear eye protection and impervious gloves when handling. Wash thoroughly after handling. Avoid breathing vapor or mist. Keep containers closed when not in use. Use only with adequate ventilation.

## **FIRST AID**

In case of contact:

**Skin** – Immediately wash skin thoroughly with mild soap and water. Remove contaminated clothing and wash before reuse. Destroy contaminated shoes and other articles made of leather.

**Eyes** – Immediately flush eyes with plenty of water for 15 minutes and get prompt medical attention.

**Inhalation** - Remove person to fresh air. Administer oxygen or artificial respiration if necessary. Call a physician.

**Ingestion** - Do not induce vomiting. Dilute with plenty of water and contact physician immediately. Never give anything by mouth to an unconscious person.

## **DISCLAIMER:**

**IMPORTANT:** The following supercedes Buyer's documents. **SELLER / MANUFACTURER MAKES NO REPRESENTATION OR WARRANTY, EXPRESS OR IMPLIED, INCLUDING OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.** No statements herein are to be construed as inducements to infringe any relevant patent. Under no circumstances shall Seller / Manufacturer be liable for incidental, consequential or indirect damages for alleged negligence, breach of warranty, strict liability, tort or contract arising in connection with the product(s). Buyer's sole remedy and Seller's sole liability for any claims shall be Buyer's purchase price. Data and results presented are based on controlled or laboratory work and must be confirmed by Buyer by testing for its intended conditions of use. The product(s) has not been tested for, and is therefore not recommended for, uses for which prolonged contact with mucous membranes, abraded skin, or blood is intended; or for uses for which implantation within the human body is intended

## **Specialty Polymers & Services, Inc. (SP&S)**

27822 Fremont

Valencia, CA 91355

[www.spolymers.com](http://www.spolymers.com)

Tel: 661-294-1790

Fax : 661-294-0640

info@spolymers.com